

Tensid uk Ltd

Maintenance for natural stone treated with PROSOCO STMP

Initial Application:

1. Ensure area is clean and free of dust and grease
2. Apply first coat of STMP to saturation by lower pressure sprayer, sponge, roller or brush – surface should remain wet for 5 minutes
3. On porous substrates apply second coat prior to first coat drying
4. Allow to dry before permitting pedestrian traffic – 12 hours before water contact and a minimum of 48 hours before oil and food staining
5. Clean up equipment with soap and water

Maintenance:

It is recommended that PROSOCO STMC maintenance cleaner be used, which is available from Tensid. On large floor areas a scrubber dryer machine fitted with suitable pads can be used, however this will accelerate the wear on the STMP, and will therefore require re-application on a more regular basis.

Dilution Rates:

Light to medium soiling:	1:40	(Scrubber drier)
Light to medium soiling:	1:20	(manual cleaning)
Medium to heavy soiling	1:10	(manual cleaning)
Heavy Soiling	1:5	(manual cleaning)

Stain Removal:

It is always advisable to clean stains as quickly as possible after the spill, this is particularly important on stains caused by red wine on porous substrates.

Stains can generally be removed using a higher concentrate of STMC, the area should always be neutralised with water.

Re-application of STMP:

Re-application is usually required between 12 months and 3 years. It varies according to traffic, cleaning schedules, methods and the amount of stain removal that has been carried out.

Method:

1. Ensure Surface is clean and dry
2. Apply in the same method as for initial application – one coat is usually sufficient

NB: Always refer to data sheets and msds before application